

multi purpose, bituminous rigid insulation board



AREAS OF APPLICATION

Multi purpose insulation board from natural wood fibre for roof, wall and floor applications.









STORAGE / TRANSPORT

flat, level and under cover protect edges from damage remove plastic foil packing only when the pallet is on hard, dry and even ground

- high compression strength
- high heat protection during summer months
- excellent insulation qualities
- water vapour open
- reduced short-term moisture absorption
- easy to handle
- suitable as insulation board for mastic asphalt screed
- · ecological and environmentally friendly
- recycleable

For more information please visit our website at www.steico.com







PACKAGING

Thickness [mm]	Size [mm]	Weight [kg/m²]	Pieces/Pallet	m² / Pallet	Weight / Pal. [kg]
10	2500 * 1200	2.20	114	342.0	approx. 790
12	2500 * 1200	2.64	95	285.0	approx. 790
15	2500 * 1200	3.30	76	228.0	approx. 790
19	2500 * 1200	4.18	60	180.0	approx. 790

CHARACTERISTIC VALUES STEICOphaltex

MATERIAL

Wood fibre insulation board produced in accordance with EN 13986 and 622-4 and with ongoing quality supervision.

Our wood fibre is sourced from effectively managed forests and is independently certified in accordance with the guidelines of the FSC®.

For dust extraction please refer to national requirements

Produced and supervised according to EN 1398	86				
porous wood fibre insulation board according to EN 622-4					
Board designation	EN 622-4 SB-E1				
Edge design	straight				
Fire class according to EN 13501-1	E				
Declared thermal conductivity λ_D [W/(m*K)]	0,05				
Declared thermal resistance R _D [(m ² *K)/W]	0,2/0,24/0,3/0,38				
Density [kg/m³]	approx. 230				
Water vapour diffusion resistance factor μ	5				
Sd value[m]	0.05/0.06/0.08/0.1				
Specific heat capacity c [J/(kg*K)]	2100				
Raw material	wood fibre, bitumen, paraffin, water repellent ingredients				
Waste code (FAK)	030105/170201				







Operating site certified according to ISO 9001:2000



Your STEICO Agent

www.steico.com

Date 12/2010. Valid to subsequent revisions.